

Dublin Kollektion



Möbel &
Polster



Schuhe



Kleidung



Täschnerie



Automobil



Flugzeug &
Boot

Prüfverfahren & Ergebnisse Tests & Results

Abriebfestigkeit nach Veslic
Color fastness to rubbing

Trocken / Dry - 50 Z
Nass / Wet - 10 Z

gemäß / according to
DIN EN ISO 11640

> = 3 (Blauskala / Grauskala)
> = 3 (Blauskala / Grauskala)

Lichtechtheit unter künstlichem Licht mit
16.000 kJ/m²
Color fastness to artificial light with exposition
energy 16,000 kJ/m²

gemäß / according to
DIN EN ISO 105 B02 (Met.5)

> = 2 ((Blauskala / Grauskala)

Dauerbiegefestigkeit bei 50.000 Zyklen
Flexing endurance at 50,000 cycles

gemäß / according to
DIN EN ISO 5402

Kein Schaden / No damage

Weiterreißfestigkeit
Tear strength

gemäß / according to
DIN EN ISO 3377-1

> = 20 (N)

Chromgegerbtes, vollnarbiges Rindsnappaleder, durchgefärbt, mit samtig glattem, weichem Griff und angenehmem Hautgefühl; ideal geeignet für die Verwendung im Möbelbereich sowie für Bekleidungs- und Modeartikel; Rohware aus europäischer Herkunft, gegerbt in Italien; Stärke: 0,9 - 1,1 mm; durchschnittliche Größe einer halben Haut: 2,4 - 2,7 m²; 61 Farben;

Chrome tanned bovine nappa leather, through dyed, with full grain and a silky smooth, soft touch and pleasant wearing comfort; perfect for use in furniture and upholstery as well as in clothing and fashion articles; hide originating from Europe, tanned in Italy; thickness: 0.9 - 1.1 mm; size of average hide: 2.4 - 2.7 m²; 61 colors;